Exhibit A regarding JP02-201904 -Takeshi



Exhibit B regarding the present application









Exhibit A Condition

Item	Example 1		Example 2		Example 3		Example 4	
Particle material	Fe		Fe		Fe		Fe	
Particle size*	30-50nm or 10um		30-50nm or 10um		30-50nm or 10um		30-50nm or 10um	
Matrix material	Polybutene		Polystyrene		Polybutene		Polystyrene	
Volume content of particle	60-95 vol. %		60-95 vol. %		60-95 vol. %		60-95 vol. %	
Film thickness (um)	5		5		5		5	
Saturation magnetization (T)	1.5		1.6		1.4		1.5	
Electrical resistivity (u Ω cm)	180		250		400		200	
Anisotropic magnetic field (Oe)**	7		10		10		8	
Permeability at 0.1 MHz	2000	2140***	1800	1600***	1500	1400***	2000	1880***
at 25 MHz	1000	2130***	1200	1590***	1300	1390***	1200	1870***
at 1GHz	-	error***	-	error***	-	error***	-	error***

* No data in JP02-201904-Takeshi and estimated from FIG. 6 of the attached reference 1.

** No data in JP02-201904 Takeshi and estimated using LLG equation.

*** Calculated using LLG equation with the parameters of film thickness, saturation magnetization, electrical resistivity and anisotropic magnetic field.

"error" represents the value of zero.

Exhibit B Condition

Item	Example 1		Example 2		Example 3		Example 4	
Particle material	Co69Fe31 (at. %)		Fe		Fe		Co69Fe31 (at. %)	
Particle size	7nm		7nm		10nm		9nm	
Matrix material	Polyimide		Polyimide		Polyimide		Teflon	
Volume content of particle	80 vol.%		80 vol.%		90 vol.%		88 vol.%	
Film thickness (um)	0.45		0.45		0.45		0.43	
Saturation magnetization (T)	1.33		1.21		1.75		1.73	
Electrical resistivity (u Ω cm)	260		250		110		100	
Anisotropic magnetic field (Oe)	75		70		70		75	
Permeability at 0.1 MHz	-	175***	-	170***	-	250***	-	230***
at 25 MHz	-	175***	-	170***	-	250***	-	230***
at 1GHz	200	195***	200	195***	250	270***	200	245***

*** Calculated using LLG equation with the parameters of film thickness, saturation magnetization, electrical resistivity and anisotropic magnetic field.

Particle size of Takeshi was estimated from FIG. 6 of the attached reference 1 and the value of coercive force shown in Table 1 of Takeshi. The estimated particle size of Takeshi was 30-50nm or 10um. As Takeshi mentions that the ferromagnetic metal particles have a column structure, the latter value of 10um can be adopted. The ferromagnetic metal particles with a size of 30-50nm never have a column structure.

If the values of 30-50nm are adopted in Takeshi, similar results will be obtained. Even if the value of 20nm proposed by Fujimori are adopted in Takeshi, similar results will be obtained. That is, the estimated permeability at 1GHz will be zero (error).

FIG. 6 of the attached Reference 1



Fig. 6 Grain size and coercivity H_c for various soft magnetic metallic alloys.

[Ref] G. Herzer, "Grain Size Dependence of Coercivity and Permeability in Nanocrystalline Ferromagnets", IEEE Trans. Mag., 26(5), 1397-1402 (1990)

2010/12/28